



# 检测报告

## Test Report

送检企业: 景德镇市英才科技有限公司

样品名称: 电脑电窑轻质耐火砖

检验类别: 委托检验



厦门泓益检测有限公司

Xiamen Hongyi Testing Technology Co., Ltd

This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of Hongyi Testing, this test report shall not be copied except in full and published as advertisement Hongyi Physical & Chemical Lab.

厦门泓益检测有限公司

Xiamen Hongyi Testing Co., Ltd.

地址: 福建省厦门市同安区轻工食品工业区美禾路 99 号

ADDRESS: No. 99 Meihe Road, Light Industry Food Industrial Zone, Tongan District, Xiamen City, Fujian Province,

邮箱: hongyotest@123.com



样品名称	: 电脑电窑轻质耐火砖	型号规格	: DG-02、DG-05、DG-08、DG-13、 DG-13、DG-24、DG-30、DG-40、 DG-50
商标	: 	样品数量	: 1 组
委托单位	: 景德镇市英才科技有限公司		
委托单位地址	: 江西省景德镇市浮梁县湘湖工业小区 110KV 变电站西侧		
生产单位	: 景德镇市英才科技有限公司		
生产单位地址	: 江西省景德镇市浮梁县湘湖工业小区 110KV 变电站西侧		
检验类别	: 委托检验	测试日期	: 2025 年 11 月 02 日-2025 年 11 月 12 日
签发日期	: 2025 年 11 月 12 日		
检验依据	: GB / T21114-2019 耐火材料 X 射线荧光光谱化学分析熔铸玻璃片法 GB/ T5988-2007 耐火材料加热永久线变化试验方法 GB/T 2997 - 2015 用于测显气孔率、体积密度 GB/T 5072 - 2008 规范常温耐压强度试验 GB/T46172 - 2025 测热平衡与热效率		
检验项目	: 见后续		
样品特征和状态	: 完好		
环境温度	: 24.6℃	环境湿度	: 62%
测试结果	: 本次委托检验, 所检项目全部符合标准要求		



报告编制: 张华伟

报告审核: 杨泽群

报告签发: 杨泽群

This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of Hongyi Testing, this test report shall not be copied except in full and published as advertisement Hongyi Physical & Chemical Lab.



序号	检测项目		单位	技术要求	检测结果	单项结论
1	耐火材料加热永久线变化测定	加热永久线变化率	%	-2.0~1.0	+0.3	合格
2	体积密度		g/cm <sup>3</sup>	≤0.8	0.7	合格
3	常温耐压强度		MPa	≥0.5	0.52	合格
4	导热系数		W/(m·K)	≤0.35	0.28 (保持 60℃ 以下)	合格
5	加热速率		min	0.1 - 30℃	0.1 - 30℃	合格



This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of Hongyi Testing, this test report shall not be copied except in full and published as advertisement Hongyi Physical & Chemical Lab.



## 注意事项:

1. 报告无“检验报告章”或检验单位公章无效。
2. 未经本实验室书面同意,不得部分复制本报告。
3. 报告无主检、审核、批准人签字无效。
4. 报告涂改无效。
5. 对检测报告若有异议,应于收到报告之日起十五日内向检测单位提出,逾期不予受理。
6. 委托检测仪对来样负责。

地址:福建省厦门市同安区轻工食品工业区美禾路 99 号

Addr: No. 99 Meihe Road, Light Industry Food Industrial Zone, Tongan District, Xiamen City, Fujian Province,

\*\*\*报告结束\*\*\*

This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of Hongyi Testing, this test report shall not be copied except in full and published as advertisement Hongyi Physical & Chemical Lab.

厦门泓益检测有限公司

Xiamen Hongyi Testing Co., Ltd.

地址:福建省厦门市同安区轻工食品工业区美禾路 99 号

ADDRESS: No. 99 Meihe Road, Light Industry Food Industrial Zone, Tongan District, Xiamen City, Fujian Province,

邮箱: hongyotest@123.com